



AMENDMENT TO THE CLAIMS:

RECEIVED
MAY 23 2003
GROUP 1700

1. (twice amended) A two-stage transfer **for application to the interior surface of a rotational mold** [useful] to impart indicia to **a polyolefin product** [products] molded in **said** [a] rotational mold at a molding temperature and ejected from the rotational at a demolding temperature less than the molding temperature, said transfer comprising:

- a. a carrier sheet of a flexible material having an indicia area for reception of said indicia;
- b. an indicia coat, in a preselected indicia array consisting essentially of a mixture of indicia material and hydrocarbon wax overlying said indicia area; and
- d. a top coat of a pressure sensitive adhesive which is substantially non-adhesive at ambient temperature and adhesive at said demolding temperature substantially covering said indicia area and overlying said indicia coat; and

said indicia and top coats having melting temperatures less than said molding temperature **to transfer to and become permanently incorporated into the surface of said polyolefin product, leaving no significant amount of residue on said mold surface.**

2. (twice amended) The transfer of claim **8** [1] including a backing coat of a pressure sensitive adhesive which bonds to the carrier sheet at ambient temperatures and releases from the carrier sheet at said demolding temperature between said indicia coat and said carrier sheet. substantially covering said indicia.

3. (previously amended) The transfer of claim 2 wherein the melting temperature of the backing coat pressure sensitive adhesive is less than said molding temperature.

Copy

4. (canceled)

5. (canceled)

6. (previously amended) The transfer of claim 2 wherein said backing and top coats extend peripherally beyond said indicia area, thereby encapsulating said indicia coat within said backing and top coats.

7. (previously amended) The transfer of claim 2 wherein said indicia coat is a mixture of from 30 to 99 weight percent hydrocarbon wax and from 1 to 70 weight percent colorant

8. (previously amended) The transfer of claim 1 wherein said polyolefin is polyethylene.

9. (withdrawn)

10. (withdrawn)

11. (withdrawn)

12. (withdrawn)

13. (withdrawn)

14. (withdrawn)

15. (withdrawn)

16. (amended) The transfer of claim 8 [1] wherein said top coat adhesive is a hydrocarbon resin.

17. The transfer of claim 2 wherein said backing coat adhesive is a hydrocarbon wax.
